

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
11 January 2001 (11.01.2001)

PCT

(10) International Publication Number
WO 01/02444 A1

(51) International Patent Classification⁶: C08F 4/12, 4/16,
10/06, C08K 5/3432, 3/10

(21) International Application Number: PCT/US99/15235

(22) International Filing Date: 6 July 1999 (06.07.1999)

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant: HUNTSMAN POLYMERS CORPORATION [US/US]; 500 Huntsman Way, Salt Lake City, UT 84108 (US).

(72) Inventors: SUN, Lixin; 4100 Tanglewood #255, Odessa, TX 79762 (US). ALLEN, George, C.; 1617 Tanglewood, Odessa, TX 79761 (US). HUGHES, Michael, P.; 2800 Teakwood, Odessa, TX 79761 (US).

(74) Agents: FANUCCI, Allan, A. et al.; Pennie & Edmonds LLP, 1155 Avenue of the Americas, New York, NY 10036 (US).

(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/02444 A1

(54) Title: OLEFIN POLYMERIZATION PROCESS AND PRODUCTS THEREOF

(57) Abstract: Methods of producing polyolefin polymers by polymerizing an α -olefin in the presence of a catalyst including a pro-catalyst having a magnesium halide, an aluminum halide, a tetravalent titanium halide, an electron donor, and a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, wherein R_1 and R_2 are each H, C_{1-4} alkyl, aryl, C_{5-12} cycloalkyl, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-4} alkyl, or a mono- or di-substituted C_{1-4} alkyl, and a co-catalyst comprising an organometallic compound, or reaction products of the pro-catalyst and the co-catalyst, wherein the electron donor is present in an amount sufficient to reduce the stickiness of the resultant polyolefin polymers. Moreover, the polymers produced thereby, and methods of preparing resultant products from the polymers are part of the present invention.

OLEFIN POLYMERIZATION PROCESS AND PRODUCTS THEREOFTECHNICAL FIELD

This invention relates to a high-molecular weight average, polyolefin polymer having a heat of fusion of about 0.4 J/g to 75 J/g, a polydispersity index of less than about 10, and a melt flow rate of between about 0.3 g / 10 min. to about 30 g / 10 min. at 230°C, having a reduced stickiness, as well as methods of producing such polyolefin polymers and products using the same by polymerizing an α -olefin in the presence of a catalyst.

BACKGROUND OF THE INVENTION

It is well known that crystalline polypropylene generally has an isotactic or syndiotactic structure and that amorphous polypropylene generally has considerable atactic structure. U.S. Pat. Nos. 3,112,300 and 3,112,301, for example, describe isotactic polypropylene and provide structural formulae for isotactic and syndiotactic polypropylene. The former is a straight chain of propylene units wherein the methyl groups are all aligned on one side of the polymer chain. In the latter, the methyl groups alternate from one side of the chain to the other. In these polypropylenes, the regularity of structure tends to result in a more highly crystalline material. Historically, atactic polypropylene polymers have a low MW, typically resulting in gummy materials of minimal tensile strength.

High-molecular-weight amorphous poly alpha-olefins ("APAO"), such as amorphous propylene homo- and co-polymers, are important for their use in diverse products. The broad utility of these materials is due in large part to the unique combination of chemical and physical properties, such as chemical inertness, softness, flexibility, etc., exhibited by these materials. Amorphous polypropylene is different from crystalline polypropylenes in steric microstructure.

Almost all of the polypropylene which is used commercially is crystalline isotactic polypropylene.

Conventional polymers of this type typically have a crystallinity, or heat of fusion, of 70 J/g or higher, and more typically 90 J/g or higher. These products are well known and have been the subject of many patents and articles.

5 The below-mentioned patents disclose one type of catalyst used in the formation of such polymers, which includes a pro-catalyst that is typically formed from the reaction product of a magnesium alkoxide compound, preferably one of the formula MgR_1R_2 , where R_1 is an alkoxy or aryl oxide
10 group and R_2 is an alkoxide or an aryl oxide group or halogen, and a tetravalent titanium halide wherein the reaction takes place in the presence of an electron donor and, preferably, a halogenated hydrocarbon.

U.S. Patent No. 5,118,768 discloses a process for
15 the production of elastomeric, primarily isotactic polyolefins by polymerizing olefins in the presence of a catalyst which includes: (a) the reaction product of a magnesium alkoxide having a formula of MgR_1R_2 , where R_1 is an alkoxy or aryl oxide group and R_2 is an alkoxide or an aryl
20 oxide group or halogen and a tetravalent titanium halide and wherein the reaction takes place in the presence of an electron donor that is an effectively hindered heterocyclic aromatic nitrogen compound, and (b) an organoaluminum compound. A variety of electron donors are disclosed,
25 including 2,6-lutidine and 6-chloro-2-picoline. U.S. Patent No. 5,164,352 has an identical disclosure, but it is directed to the catalyst used in the polymerization of these polyolefins. Both references disclose that the catalyst production occurs in a liquid reaction medium, which must be
30 followed by elaborate steps to suitably isolate the catalyst from the reaction solvent(s). The polymerization reaction also occurs in the liquid phase at a temperature of 50°C to 80°C and a pressure sufficient to maintain liquid conditions.

U.S. Patent Nos. 5,089,573, 5,118,649, 5,118,767,
35 and 5,294,581, all similarly require magnesium alkoxide and/or magnesium aryl oxide. These references are

substantially similar to U.S. Patents Nos. 5,118,768 and 5,164,352.

U.S. Patent Nos. 5,438,110 and 4,990,479 disclose a polymerization process that involves polymerizing or
5 copolymerizing olefins in the presence of an olefin polymerization catalyst formed from: (A) a solid titanium component which contains magnesium, titanium, halogen and an electron donor as the essential components, where the magnesium compound or magnesium compound with the electron
10 donor is reacted with titanium in the liquid phase, (B) an organoaluminum compound, and (C) an organosilicon compound represented by the formula $\text{SiR}^{21}\text{R}^{22}_m(\text{OR}^{23})_{3-m}$, where R^{21} is a cyclopentyl group, a substituted cyclopentyl group, or one of several other ringed structures.

U.S. Patent No. 5,218,052 discloses a method for making a homopolymer of propylene having increased stiffness and a broadened, molecular weight distribution by
15 polymerizing propylene in a high activity catalyst system and a silane in at least two stages. That system includes: (a) a silane of formula $\text{R}_1(\text{R}_2)_2\text{Si}(\text{OR}_4)(\text{OR}_5)_2$; (b) a titanium-containing compound supported on a magnesium-containing compound; and (c) a co-catalyst comprising a Group II or III metal alkyl. Lutidine is disclosed among a vast genus of possible electron donors.

U.S. Patent No. 5,182,245 discloses a solid, hydrocarbon-insoluble catalyst or catalyst component for the polymerization of alpha-olefins in the slurry phase, from a product produced by: (A) forming a solution of magnesium-containing species in a liquid, (B) precipitating solid
25 particles from the solution by treatment with a transition metal halide in the presence of at least one of a tetrabutoxysilane and a tetrabutoxytitanate; and (C) treating the particles with a transition metal compound and an electron donor. Lutidine is disclosed as a possible electron
30 donor among a vast genus of possible electron donors.

U.S. Patent No. 5,153,158 discloses: (I) an olefin polymerization catalyst formed by prepolymerization of olefin

and an olefin polymerization catalyst of a solid titanium catalyst component (A) having magnesium, titanium, and halogen as essential ingredients, along with (B) a Group I or III metal organometallic compound and (C) an electron donor selected from diethers and organosilicons represented by $R_4Si(OR')_4$, and being suspended in a liquid alpha-olefin, and (II) a metal organometallic compound of a Group I or III metal. The R_1 group is disclosed in the specification to be one of various cyclopentyl or substituted cyclopentyl groups.

10 U.S. Patent No. 4,990,477 is essentially cumulative, except that it discloses that the optional electron donor may instead be an organic carboxylic acid.

European Patent 475,307 discloses an elastomeric high molecular weight substantially amorphous propylene homopolymer having a melting point between about 145°C and 165°C, a melt viscosity at 190°C of greater than 200,000 cPs, a heat of fusion of about 16.7 J/g to 41.8 J/g, having about a 35% to 55% diethyl ether soluble fraction, which fraction has inherent viscosity less than about 1.0 dl/g and is

20 substantially free of isotactic crystallinity.

Amorphous polypropylenes, which have very little strength, are used commercially in adhesives and asphalt additives, for example. Conventional amorphous polypropylenes that tend to have a crystallinity lower than 65 J/g typically have an extremely high melt flow rate of around 10,000 g/10 min. (at 230°C). Generally, these amorphous polypropylene polyolefins are sticky, which limits their possible usage in commercial products. Conventional heterogeneous Ziegler-Natta catalysts, such as those

30 disclosed in U.S. Patent No. 4,347,158, for example, tend to produce tacky polymers that have a broad range of molecular weights and tacticities. It would be advantageous to reduce this stickiness in the polyolefins and to produce polyolefins having a low degree of crystallinity and a lower melt flow

35 rate, thereby creating a class of polymers having a variety of new uses.

It is thus desired to produce higher molecular weight FPO polymers that have a low crystallinity, low solubility in methylethyl ketone, and a low melt flow rate ("MFR").

5

SUMMARY OF THE INVENTION

The present invention relates to a method of preparing polyolefin polymers by polymerizing an α -olefin monomeric raw material in the presence of a catalyst having a pro-catalyst of
10 a magnesium halide, an aluminum halide, a tetravalent titanium halide, an electron donor, and a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, wherein R_1 and R_2 are each an H, C_{1-6} alkyl, aryl, C_{5-12} cycloalkyl, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-6} alkyl, or a mono- or di-
15 substituted C_{1-6} alkyl, and a co-catalyst comprising an organometallic compound, or reaction products of the pro-catalyst and the co-catalyst, wherein the electron donor is present in an amount sufficient to reduce the stickiness of the resultant flexible polyolefin polymers.

20

In another embodiment, the method further includes selecting the monomeric raw material to be a plurality of alpha-olefin monomers. In another embodiment, the method further includes selecting the plurality of alpha-olefin monomers to be monomers of propylene, ethylene, butene, pentene, octene, or
25 mixtures thereof. In yet another embodiment, the method further includes selecting the plurality of alpha-olefin monomers to be propylene and at least one additional monomer having between about 2 to 12 carbon atoms per molecule. In a preferred embodiment, the additional monomer is selected to be at least
30 one of ethylene, 1-butene, 1-pentene or 1-octene.

In one embodiment, ethylene is provided in the monomeric raw material in an amount of about 1 to 40 weight percent. In another embodiment, ethylene is provided in the monomeric raw material in an amount of about 1 to 20 weight
35 percent.

In one embodiment, hydrogen is added to the polymerization in an amount of less than about 10 weight

percent. In another embodiment, the organometallic compound is selected to be a metal alkane. In a preferred embodiment, the organometallic compound is selected to be an aluminum alkane.

In another embodiment, an external modifier is added to the catalyst in an amount sufficient to increase the crystallinity of the polyolefin polymers to a desired level of between about 15 J/g to 60 J/g. In another embodiment, the desired level is between about 4.6 J/g to 35 J/g. In a preferred embodiment, the external modifier is selected to be a silane component, selecting the desired level of crystallinity to be about 25 J/g to 55 J/g, and selecting the polyolefin polymer to have a melt flow rate of between about 0.3 to 30 g / 10 min. at 230°C.

In another embodiment, ethylene is provided in an effective amount to preclude substantial modification by the external modifier of at least one physical property of the polymer. In a preferred embodiment, the physical property is selected to include crystallinity of propylene domains in the polymer.

In yet another embodiment, the melt flow rate of the polyolefin polymer is selected to be between about 0.4 J/g to 60 g / 10 min. In a more preferred embodiment, the melt flow rate is about 0.4 J/g to 15 J/g. In another embodiment, the stickiness is reduced to a sufficiently low level so that only between about 1 to 12 weight percent of the polyolefin polymer is soluble in methylethyl ketone. In a preferred embodiment, the stickiness is reduced to a sufficiently low level so that only between about 1 to 5 weight percent of the polyolefin polymer is soluble in methylethyl ketone.

In another embodiment, sufficient polymerization conditions are selected to include a feed of a plurality of monomers having at least about 70 weight percent propylene, a temperature of about 130°F to 175°F, and a reactor pressure sufficient to maintain the propylene in a liquid phase.

In another embodiment, the silane is selected to have R_1 as a C_{3-12} cycloalkyl, R_2 as C_{1-6} alkyl, and R_3 and R_4 each as a C_1 alkyl. In a preferred embodiment, the silane is selected to

have R_1 as cyclohexyl, and R_2 , R_3 , and R_4 each as methyl. In another embodiment, the external modifier is selected to be a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, wherein R_1 and R_2 are each an H, C_{1-6} alkyl, aryl, C_{3-12} cycloalkyl, each of which may be
5 unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-6} alkyl, or a mono- or di-substituted C_{1-6} alkyl. In both embodiments, the preferred aryl is a C_{6-22} aryl.

In yet another embodiment, the invention includes forming a molded product from the polymer. In a preferred
10 embodiment, the molded product is formed by injection molding or blow molding. In another embodiment, the invention includes forming a film having a thickness between about 0.5 mils to 10 mils from the polymer.

The invention also relates to a polyolefin polymer
15 produced by the process described above. Additionally, the invention relates to a high-molecular weight average, polyolefin polymer having a heat of fusion of about 0.4 J/g to 75 J/g, a polydispersity index of less than about 10, and a melt flow rate of between about 0.3 g / 10 min. to about 30 g / 10 min. at
20 230°C, having a reduced stickiness.

In one embodiment, the only about 1 to 12 weight percent of the polyolefin polymer is soluble in a methylethyl ketone solution. In a preferred embodiment, only about 1 to 5 weight percent of the polyolefin polymer is soluble in
25 methylethyl ketone.

In another embodiment, the polymer is a homopolymer of propylene. In a preferred embodiment, the polymer is a copolymer of propylene and at least one of ethylene, 1-butene, 1-pentene, and 1-octene. In another embodiment, the heat of
30 fusion is between about 4.6 J/g to 35 J/g. In a more preferred embodiment, the heat of fusion is between about 15 J/g to 60 J/g. In another embodiment, the melt flow rate is between about 0.4 g / 10 min. to 15 g / 10 min. In a preferred embodiment, the melt flow rate is between about 0.5 g / 10 min. to 7 g / 10
35 min. In yet another embodiment, the polydispersity index of the polymer is less than about 8. In another embodiment, the

polymer has a melt swell ratio of about 1.6 or less. In a preferred embodiment, the melt swell ratio is about 1.4 or less. In another embodiment, the polymer is formed to substantially maintain the same physical shape during steam autoclaving at a temperature of at least 100°C and at a pressure of at least atmospheric pressure.

The invention also relates to a method of preparing polyolefin polymers by preparing a pro-catalyst by mixing a magnesium halide, an aluminum halide, a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, an electron donor, and a tetravalent titanium halide to form a first mixture, wherein R_1 and R_2 are each an H, C_{1-6} alkyl, aryl, C_{3-12} cycloalkyl, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are each an H, C_{1-6} alkyl, or a mono- or di-substituted C_{1-6} alkyl, adding a co-catalyst comprising an organometallic compound to the pro-catalyst to prepare a catalyst, contacting a monomeric raw material and the catalyst under conditions sufficient to cause polymerization of the raw material to produce a polymerization product containing polyolefin polymers, wherein the catalyst reduces the stickiness of the resultant polyolefin polymers, and recovering polyolefin polymers from the polymerization product.

DETAILED DESCRIPTION OF THE INVENTION

It has now been discovered that flexible polyolefins ("FPO"), a new class of polymers having a controllable degree of crystallinity lower than that found in commercial isotactic polypropylene, may be advantageously produced using a newly discovered catalyst as described herein. This class of polymers has various applications because of enhanced properties compared to purely amorphous polypropylenes. It is believed that low molecular weight, stereo- and regio-irregular polypropylene having atactic characteristics can be responsible for the highly sticky FPO ("flexible polyolefin") polymers obtained with conventional catalysts. Such sticky material creates a variety of handling and processing difficulties.

An improved catalyst for the production of these flexible polyolefins has now been discovered, which reduces

stickiness of the resultant FPO polymers that are produced. The prior art catalyst typically included a pro-catalyst made of a magnesium halide, aluminum halide, and a titanium halide. The present invention adds a silane component, such as cyclohexylmethyldimethoxysilane. Although the inventors do not wish to be bound by any particular theory, this is believed to increase the surface area and pore volume of the magnesium halide and aluminum halide mixture, and uses one of a limited number of specific nitrogen-based donors. The Lewis acidic centers are believed to be coordinatively highly unsaturated, sterically accessible, non-chiral and non-stereospecific, thereby producing low molecular weight, atactic polymers. The surface tension of polymers increases with molecular weight and tacticity, yet the surface free energy can be reduced when the surface is covered by a layer of low molecular weight atactic polymers. Thus, the driving force in Ziegler-Natta ("Z-N") polymers permits the low molecular weight polymers to concentrate on the surface and impart stickiness. It is believed that the addition of the silane component alters the nature of the magnesium and aluminum halide components by increasing the surface area and pore volume to provide more interstitial space in the magnesium and aluminum halide components for the titanium halide to reside when it is added. A weak base, or nitrogen-based donor, and titanium halide are then added to the mixture before ball milling to form the catalyst. The base is believed to advantageously complex to a portion of titanium sites, thus rendering them unable to produce low molecular weight polymers that typically cause stickiness in flexible polyolefin polymers. By decreasing the formation of lower molecular weight FPO polymers, which are more sticky than higher molecular weight FPO polymers, and by narrowing the band of molecular weights of the polymer product, an improved polyolefin may be produced having reduced stickiness and improved processing characteristics.

35 The improved FPO polymers of the present invention advantageously have a low crystallinity in the range of about 0.4 J/g to 75 J/g, although this is preferably about 4.6 J/g to

35 J/g or 15 J/g to 60 J/g, depending upon the desired end use of the polymer. The polymers also have a melt flow rate of between about 0.4 g/ 10 min. to 60 g/ 10 min., and every whole integer therebetween. Preferably, the melt flow rate is between about 0.4 g/ 10 min. to 15 g/ 10 min. and every whole integer therebetween, more preferably between about 0.4 g/ 10 min. to 7 g / 10 min., and every whole integer therebetween, and most preferably between about 0.5 g/ 10 min. to 5 g / 10 min., and every whole integer therebetween. These FPO polymers are advantageously produced by the use of a catalyst containing a pro-catalyst capable of imparting a low crystallinity and a low melt flow rate, an organometallic compound, and an external modifier that is capable of increasing the low crystallinity up to as high as 60 J/g, depending upon the amount of external modifier included in the catalyst. These FPO polymers have the advantageous property of being steam sterilizable and, therefore, capable of substantially retaining their shape, which other polymers typically cannot do subsequent to steam sterilization.

Internal electron donors, useful for preparing pro-catalysts as in the present invention, are generally categorized into two types: Type I and Type II. Type I internal donors are used to increase the pro-catalyst surface area and, subsequently, the catalyst activity. During the mechanical pulverization by ball milling, the magnesium halide, such as $MgCl_2$, is broken into small crystallites, causing an increase in surface area. However, when the particle size is reduced beyond a certain point, reaggregation of particles occurs due to the increasing surface free energy, thereby preventing further reduction of particle size. The addition of a Type I donor can reduce the surface free energy and, therefore, facilitate the further disintegration of particles. These Type I donors are commonly used in Z-N catalysts. At very low dosage, they may enhance the catalyst activity because of the increased surface area, but when the dosage increases they start to poison the specific active sites. This results in lower catalyst activity, higher isotacticity and higher molecular weight. However, an

increased donor dosage is typically and undesirably accompanied by an increased heat of fusion of the polymer. Thus, it would be advantageous for the Type I donor to provide a maximum productivity increase with the least change in heat of fusion.

5 The silane donors of the present invention advantageously accomplish these dual goals when combined with other ingredients to form the pro-catalyst.

Type II internal donors, on the other hand, are used to increase the molecular weight and reduce the low molecular
10 weight ("LMW") fractions that cause the stickiness typically associated with polyolefin polymers. This may be accomplished by either selectively poisoning the active sites that produce the LMW fractions, or depressing the chain transfer reactions on these active sites, while not increasing the crystallinity
15 of the polymer product to any significant extent. It has now been found that some weak Lewis bases, such as certain nitrogen-based donors like 2,6-lutidine and 6-chloro-2-picoline, are effective as Type II donors to increase the molecular weight of polymers without, or not significantly, affecting the
20 crystallinity. They accomplish this by selectively blocking many of the most acidic sites that produce LMW, atactic fractions while also depressing the chain transfer reaction without substantially increasing overall crystallinity. Even these advantageous Type II donors negatively impact on catalyst
25 productivity.

The catalyst includes a pro-catalyst component and an organometallic component, and preferably also includes an external modifier. The pro-catalyst includes a magnesium halide, an aluminum halide, a tetravalent titanium halide, a
30 particular nitrogen-based electron donor, and an internal modifier that is typically a silane component.

In forming the catalyst, any titanium halide is suitable for mixing with the magnesium and aluminum halides, although titanium tetrahalides are preferred and titanium
35 tetrachloride is most preferred. Although any aluminum halide is suitable for use in the catalyst, aluminum trichloride is preferred. Similarly, although any magnesium halide is suitable

for use in the catalyst, magnesium dichloride is preferred. The aluminum and magnesium halides may be solid or liquid when mixed, but they are preferably solid. The titanium halide is preferably a liquid when added, as are the electron donor and
5 the silane component.

Although any internal electron donor, as understood by those of ordinary skill in the art, is suitable for use in the catalyst, the Type II internal donor is preferably a nitrogen-based Lewis base. The Lewis base, or electron donor,
10 is more preferably selected from the following: 2,3-dimethylquinoxaline, quinaldine, 2,6-lutidine, 2,4,6-collidine, tetramethylpyrazine, 2,4-dimethylquinoline, 2,6-dichloropyridine, 2-chloroquinoline, 2-chloro-6-methoxypyridine, 2,3-dichloroquinoxaline, 2,4,6-trichloropyrimidine, 2,4,5,6-
15 tetra-chloropyrimidine, 2-chlorolepidine and 6-chloro-2-picoline, and the donor is most preferably 2,6-lutidine, 2,6-dichloropyridine, 6-chloro-2-picoline, or mixtures thereof. No specific amount of Lewis base, or internal electron donor, may be specified in the abstract for use in the catalyst, because
20 the amounts used are relative to amounts of other ingredients in the catalyst recipe. Thus, amounts of the various components must be quantified by the molar ratio relative to each other.

The relative amounts of each component in the catalyst can vary over well defined ranges. Specifically, the molar
25 ratio of Mg:Al:Si:N:Ti is about 8:0.01:0.01:0.2:1 to 80:30:0.5:1.2:1, preferably 12:1:0.1:0.3:1 to 70:25:0.4:1:1 Mg:Al:Si:N:Ti. In a more preferred embodiment, the molar ratio of Mg:Al:Si:N:Ti is about 14.9:1.9:0.2:0.6:1. In these ratios, Mg, Al and Ti designate halides, Si designates the silane
30 component and N designates the nitrogen donor. One of ordinary skill in the art is well aware of how to vary the amounts of the different components to achieve the desired ratios set forth above.

Catalyst preparation typically begins with the
35 magnesium halide and aluminum halide being combined, preferably with some degree of mixing, although this is not required. The preparation occurs around room temperature, although the exact

temperature is not a crucial aspect of the invention. The silane component, or internal modifier, is typically in liquid phase and may be added to the halide combination. The silane component has a formula of $R_1R_2Si(OR_3)(OR_4)$, wherein R_1 and R_2 are each an H, C_{1-4} alkyl, aryl, C_{6-12} cycloalkyl, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-4} alkyl, or a mono- or di-substituted C_{1-4} alkyl. A preferred aryl is C_{6-22} aryl. Preferably, R_1 is C_{6-12} cycloalkyl or a mono- or di-substituted C_{6-12} cycloalkyl, R_2 is H or methyl, more preferably R_1 is an unsubstituted C_{6-12} cycloalkyl, and most preferably is cyclohexyl. R_2 is more preferably methyl. R_3 and R_4 are preferably an unsubstituted C_{1-4} alkyl, more preferably methyl or ethyl, and most preferably methyl. The silane is preferably added by spraying over the halide combination, or some other form of vaporizing, to increase the surface area and contact between the components. As discussed above, the silane component is believed to alter the nature of the magnesium and aluminum halide components by increasing the surface area and pore volume to provide more interstitial space in the magnesium and aluminum halide components for the titanium halide to reside when it is added. The amount of silane added falls within the molar ratio range discussed above.

The silane and halides are preferably mixed, and more preferably pulverized in a ball mill or other suitable vessel to form a first mixture before additional components are added. Ball milling typically involves the tumbling or vibrating of steel or other inert metallic or inert ceramic balls to pound the halide particles and the silane together. The ball milling of the solid pro-catalyst component is preferably accomplished in a 1L stainless steel rotary mill pot filled to about 50 volume percent with 1/2" stainless steel balls. It is well understood by those skilled in the art that the specific size of the pot, the ball material, the component phase, and the volume percent filled may be varied as desired.

Although the specific catalyst particle size is not essential, smaller catalyst particle size is believed to be

enhance the efficiency of the catalyst. Any length of milling time is sufficient, although it is preferred that the mixing occur over a period of about 4 to 40 hours, more preferably about 8 to 30 hours, and most preferably about 12 to 25 hours.

5 After ball milling, an electron donor and a titanium halide are combined with the mixture from the initial ball milling. The specific amounts added are determined relative to the other catalyst ingredients, and fall within the molar ratio range described herein. The donor and titanium halide are both
10 preferably liquid, and may be added at once or slowly while all the catalyst ingredients are mixed. They are preferably sprayed into the ball mill or other vessel, although any means of adding them to the first mixture is acceptable. The combination of the electron donor, titanium halide, and first mixture is then
15 mixed, preferably by ball milling. Again, any length of time is sufficient for this mixing stage, although it is preferred that the mixing occur over a period of about 4 to 40 hours, more preferably about 8 to 30 hours, and most preferably about 12 to 25 hours. Example 54 below provides a sample catalyst recipe.

20 It is well known that supported coordination pro-catalysts and catalyst systems of the type used herein are highly sensitive, in varying degrees, to catalyst poisons such as moisture, oxygen, carbon oxides, acetylenic compounds and sulfur compounds. It will be understood that in the practice of this
25 invention, as well as in the following examples, both the equipment and the reagents and diluents are carefully dried and free of potential catalyst poisons.

Subsequent to formation of the pro-catalyst, the pro-catalyst is combined with a co-catalyst and optionally with an
30 external modifier, to produce flexible polyolefins having reduced tackiness. In addition to the pro-catalyst, a primary organometallic compound, preferably a metallic alkane, and more preferably an aluminum alkane, to be employed as a co-catalyst may be chosen from any of the known activators in olefin
35 polymerization catalyst systems comprising a titanium halide, preferably free of halogens. While aluminum trialkyl compounds, dialkylaluminum halides and dialkylaluminum alkoxides may be

used, it is preferable to use aluminumtrialkyl compounds, more preferably those wherein each of the alkyl groups has 1 to 6 carbon atoms, e.g., aluminumtrimethyl, aluminumtriethyl, aluminumtri-n-propyl, aluminumtri-isobutyl, aluminumtri-isopropyl and aluminumdibutyl-n-amyl. Alternatively, these may be used in combination with various alkyl aluminum halides, e.g., diethyl aluminum chloride. In the most preferred embodiment, aluminum triethyl is used as the co-catalyst.

The external modifier may be any silane modifier, but is preferably a silane having a formula of $R_1R_2Si(OR_3)(OR_4)$, wherein R_1 and R_2 are each an H, C_{1-6} alkyl, aryl, C_{3-12} cycloalkyl, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-6} alkyl, or a mono- or di-substituted C_{1-6} alkyl. A preferred aryl is a C_{6-22} aryl. Preferably, R_1 is C_{6-12} cycloalkyl or a mono- or di-substituted C_{6-12} cycloalkyl, R_2 is H or methyl, more preferably R_1 is an unsubstituted C_{6-12} cycloalkyl, and most preferably is cyclohexyl. R_2 is more preferably methyl. R_3 and R_4 are preferably an unsubstituted C_{1-6} alkyl, more preferably methyl or ethyl, and most preferably methyl. Most preferably, the external modifier is identical to the internal modifier used in the pro-catalyst. Increasing the amount of external modifier typically increases the crystallinity in the polymer ultimately produced. The pro-catalyst with co-catalyst in the absence of an external modifier is capable of producing an FPO polymer with a H_i at a lower range of about 4.6 J/g to 60 J/g, preferably around 15 J/g to 30 J/g, and this may be adjusted upward by increasing the amount of external modifier added to the catalyst up to an H_i of about 60 J/g, and every whole integer therebetween. The preferred amount of external modifier is seen in the Examples below, although other useful amounts are easily determined by those of ordinary skill in the art.

The external modifier may be added in any desired ratio to advantageously provide the desired crystallinity in the FPO polymers, although the molar ratio of Si:Ti (external silane modifier to titanium in the pro-catalyst) will typically be from

0:1 up to about 4:1, and more typically be from 0:1 up to about 1:1. Besides increasing crystallinity up to a maximum of about 75 J/g, the addition of the external modifier tends to decrease the MFR. An MFR as low as 0.3 g/ 10 min. may be obtained, although the MFR is typically 0.4 g /10 min. to 60 g/ 10 min. in the FPO polymers. For example, one experiment with an Si:Ti molar ratio of 0.5:1, and an Al:Ti ratio of 200 (organometallic co-catalyst to pro-catalyst) yielded an MFR of about 3 g / 10 min., while an Si:Ti ratio of about 4:1 provided an MFR of about 0.3 g / 10 min.

To prepare the final polymerization catalyst composition, pro-catalyst, co-catalyst, and external modifier may simply be combined, most suitably employing a molar ratio of pro-catalyst to co-catalyst to produce in the final catalyst a ratio of aluminum to titanium of from about 50:1 to 600:1, preferably from about 70:1 to 400:1, and more preferably from about 80:1 to 300:1. Increasing the Al:Ti ratio may slightly increase catalyst activity at the expense of increased catalyst residue in the unextracted polymeric product. These factors should be considered in selecting the Al:Ti ratio for any given process and desired product. Based on the disclosure herein, particularly of these ratios and the ratios provided above for the pro-catalyst, one skilled in the art can prepare and use a catalyst in accordance with the invention.

While the catalysts of this invention are particularly adapted for use in continuous polymerization systems, they may, of course, also be employed in batch polymerization. When used in continuous polymerization, the catalysts are typically dumped into the reactor in amounts sufficient to replace catalyst used. The productivity of the pro-catalyst or catalyst are generally determined as g polymer/g pro-catalyst, or g polymer/ g catalyst, in a standard one hour batch reaction; it may also be expressed as kg polymer/g pro-catalyst. This measure of catalyst efficiency ("CE") is also used for continuous reactions.

Polymerization of propylene, for example, is typically conducted in a polymerization reactor with the catalysts of the

invention in a liquid system with an inert diluent such as a paraffinic liquid of 3 to 15 carbon atoms per molecule, or in a liquid system containing propylene as sole diluent or together with a small amount of propane, or in vapor phase. Propylene polymerization in liquid phase is typically conducted at a temperature of about 40°C to 80°C, more preferably 50°C to 70°C, and most preferably 55°C to 65°C, at a pressure sufficient to maintain liquid conditions. Conventional operating conditions for propylene polymerization, other than the novel catalyst preparation and use taught herein, are well known to those skilled in the art and are not essential to the production of the polymers of the present invention. In a continuous reaction system, the liquid in the reaction zone is maintained at reaction conditions, monomer is continuously charged to the reaction zone, catalyst components are also charged continuously or at frequent intervals to the reaction zone, and reaction mixture containing polymer is withdrawn from the reaction zone continuously or at frequent intervals. For example, 660 mL of propylene batch polymerized with 10 mg of catalyst at 60°C for about 1 h provided a polymer having a H_i of about 27 J/g and an MFR of about 1.6 g / 10 min. The catalyst productivity was about 15,200 g polymer per g catalyst.

Polymer Characterization

Several different families of propylene-based polymers, for example, may be prepared in a polymerization reactor. Some examples of these polymer families include, but are not limited to: isotactic propylene homopolymers, isotactic propylene/ethylene copolymers, amorphous poly- α -olefins ("APAO") propylene homopolymers, APAO propylene/ethylene copolymers, APAO propylene/butene copolymers, FPO propylene homopolymers, FPO propylene/ethylene copolymers, and FPO propylene/butene copolymers. Following the polymerization reaction, conventional processing technology required addition of large amounts of water to transport the polymer to bulky storage tanks for later processing. The FPO polymers may be processed in such a conventional manner, or they may be transported directly from

the polymerization reactor to the final extruder via a kneader-extruder device, which assists in devolatilization of unreacted monomer(s). A preferred device, which maintains a substantially constant inventory of polymer therein, is disclosed in co-pending application serial nos. 08/598,820 and 08/630,800, the disclosures of which are expressly incorporated herein by reference thereto. The polymer is fed, whether from conventional storage tanks or the novel kneader-extruder, into the final extruder. In the extruder, the polyolefin material is typically mixed with small amounts of water to deactivate any remaining catalyst(s) in the material and antioxidants. Heating the material further drives off any unreacted monomer(s), antioxidant solvents and excess steam added during this stage. Finally, the polyolefin material is typically transferred to a pelletizer where it is pelletized for storage and/or use.

The FPO polymers are typically propylene homopolymers, but they may also be propylene in a mixture with at least one other monomeric raw material, such as a C_{2-12} alkene. The other monomeric raw materials are alpha-olefins in a preferred embodiment, such as ethylene, 1-butene, 1-pentene, and 1-octene. A particularly preferred component for use with propylene is ethylene, preferably in about 1 to 40 weight percent, and more preferably in about 1 to 20 weight percent, of the polymer composition. In one embodiment, the ethylene is increased in the monomeric raw material to inhibit or substantially eliminate the effects of the external donor to varying degrees, i.e., to inhibit the ability of the external donor to increase the crystallinity of propylene domains within the polyolefin polymer.

The FPO polymers are characterized by a variety of properties. The most important of these properties are the degree of crystallinity and the degree of polymerization. Crystallinity, or heat of fusion (ΔH_f) is typically measured by ASTM Method D-3417 (DSC). The polymers of the present invention have a heat of fusion that may range from about 0.4 J/g to 75 J/g, preferably about 15 J/g to 60 J/g, and more preferably about 25 J/g to 55 J/g, and a melt flow rate of between about

0.3 to 15 g / 10 min. (at 230°C). More preferred melt flow rates are discussed herein. Products produced with the FPO polymers advantageously tend to feel softer, smoother, and more silky to the touch, rather than being more rigid, more tacky and
5 having a slightly sticky feel as with products produced using conventional catalysts. The reduced stickiness is believed to be achieved by increasing the molecular weight average, and, in particular, reducing the low molecular weight portions and decreasing the band of molecular weights. This imparts improved
10 processing characteristics to the flexible polyolefin polymers. This is also believed to be accomplished by the use of an internal modifier present in the pro-catalyst portion of the catalyst present when polymerizing the polyolefin polymers of the present invention. An example of an internal modifier is
15 the nitrogen-based electron donor of the present invention, preferably 2,6-lutidine and 6-chloro-2-picoline. When it is desired to alter the crystallinity of the polyolefin polymers, an external modifier of a silane may be added.

MFR is measured according to ASTM-D1238 standard
20 Method A/B (2.16 kg/230°C), such as on a Kayness Galaxy I Melt Indexer. The methyl ethyl ketone ("MEK") solution percent was determined by extracting about 5 g of polymer with 100 mL of boiling methyl ethyl ketone for 6 hours. Tensile tests (ASTM-D638) were performed on an Instron 1125 with Type I injection
25 molded tensile bars at test speed of 2"/min. The VICAT softening point was measured in accordance with ASTM-D1525. Shore D hardness was determined in accordance with ASTM-D2240. Percent tensile set was measured after 300 percent extension and calculated by the following equation:

30

$$\% \text{ Tensile Set} = (L_f - L_i) (L_e - L_i) \times 100\%$$

where L_i is the initial separation, L_e is the extension, and L_f is the final separation. A variety of other characteristics may
35 be used to describe these polymers as well, such as VICAT softening point of about 40°C to 75°C, and preferably 45°C to 70°C; Shore D hardness of about 30 to 65, and more preferably

about 40 to 55; tensile modulus; tensile stress; a melt swell ratio of about 1.6 or below, preferably about 1.5 or below, and most preferably about 1.4 or below; and the like. The VICAT softening point and Shore D hardness will vary depending on the melt flow rate, heat of fusion, and the like in the polymer product. The properties vary depending upon the specific FPO polymer produced, which is dependent upon the exact ratios of Al:Ti (co-catalyst to pro-catalyst) and Si:Ti (external modifier to pro-catalyst), as well as the specific silane or other similar compound used in the pro-catalyst and the external modifier. Thus, these polymers are defined primarily by means of their crystallinity, or heat of fusion, their melt flow rate, and their molecular weight distribution, or polydispersity index ("MWD" or "PDI").

The molecular weight distribution, or polydispersity index, of the FPO polymers is about 10 or lower, preferably about 9 or lower, and most preferably about 8.5 or lower. The PDI is a ratio of the molecular weight average (M_w) over the molecular number average (M_n). The melt swell ratio is measured by the ratio of the diameter of a strand of extruded polymer to the diameter of the orifice through which it was extruded. A lower melt swell ratio is an indicator of a lower PDI, which itself indicates a narrower molecular weight distribution and, therefore, a less sticky, tacky, FPO polymer product. A low PDI combined with a low melt flow rate advantageously provides the polymers of the present invention with characteristics desired in the art. For example, a low MFR is characteristic of the reduced stickiness associated with the processing of the polymer, both during production and as a final product for consumer or industrial usage. Additionally, the low MFR of the FPO polymers tends to result in a higher melt strength and higher viscosity, which vastly facilitates the production of various useful articles such as blown films. "Reduced stickiness" and "reduction in stickiness," as used herein, typically is measured by the MEK soluble fraction of the polymer. A polymer having reduced stickiness is generally where

about 1 to 12 weight percent, preferably about 2 to 5 weight percent, of the polymer is soluble in MEK.

Various additives may be included in the FPO polymers, such as antioxidants, UV stabilizers, pigments, and the like. 5 Adding or removing hydrogen during the polymerization described herein may affect the MFR of the FPO polymers, while having minimal impact on the degree of crystallinity.

A variety of products may be produced using the polymers of the present invention, such as for polymer blend 10 additives. The polymers herein may be formed as an: extrusion or extrusion coatings, such as a film extrusion, sheet extrusion, paper extrusion, aluminum foil extrusion, cellophane extrusion, or contour extrusion; molding, such as injection molding or blow molding; coating, such as wire coating or cable 15 coating; resin, such as wax fortifying resins or potting and impregnating resins; monofilaments; hot-melt adhesives; and powdered, such as rug backing powder, rotational molding powder, powder molding, protective coatings on rigid surfaces, and fabric coating powder. These methods of forming polymer 20 products and the polymer products are not exhaustive, and one of ordinary skill in the art can envision a broad array of useful products and processes to manufacture such products with a polymer of the present invention. For example, a molding is a process typically understood to provide end-products such as 25 foams, webs, sheets, films, and the like. One particularly useful polymer product is films, which are understood by those of ordinary skill in the art to have a thickness of about 0.5 mils to 10 mils. One benefit of these polymers is that they substantially maintain the same physical shape during steam 30 autoclaving. Those of ordinary skill in the art will readily understand the conditions under which steam autoclaving occurs, typically at temperatures of at least 100°C and pressures of at least atmospheric pressure.

35

EXAMPLES

The invention is further defined by reference to the following examples describing in detail the preparation of the

compounds and compositions of the present invention. It will be apparent to those skilled in the art that many modifications, both to materials and methods, may be practiced without departing from the purpose and interest of this invention.

5 A variety of catalysts for the preparation of FPO polymers were prepared and tested. Polymerization tests were conducted in liquid polypropylene in a 1.0 L stainless steel autoclave equipped with an agitator. After the reactor was thoroughly purged with nitrogen to remove any catalyst poisons,
10 such as moisture and oxygen, 10 mg of solid pro-catalyst component were charged into the reactor as a 1 weight percent mixture in dry mineral oil, followed by addition of triethylaluminum co-catalyst in a prescribed amount to obtain an Al/Ti molar ratio of about 200:1. 300 g of liquid propylene
15 were then charged into the reactor and the polymerization proceeded at 60°C for one hour under agitation sufficient to mix the components. At the end of the hour, the unreacted propylene was vented off and the polymer product was recovered.

The "C-Donor" was cyclohexylmethyldimethoxysilane, and
20 "D-Donor" was dicyclopentyldimethoxysilane.

EXAMPLES 1-2: Conventional Catalysts

A conventional catalyst may be prepared according to the disclosure of U.S. Patent Nos. 4,347,158. Example 1 of the
25 '158 patent describes such a catalyst preparation as follows. Anhydrous $MgCl_2$ was prepared by drying at 350°C for 4 hours under an HCl blanket. 25 grams of this anhydrous $MgCl_2$, 4.34 g $AlCl_3$, and 7.01 g anisole were charged under nitrogen atmosphere into a vibrating ball mill having a 0.6 L capacity containing
30 316 stainless steel balls weighing a total of 3250 g and each having a diameter of 12 mm. This mixture was co-comminuted for 24 hours without temperature control. Titanium tetrachloride was precomplexed with ethyl benzoate (EB) in n-heptane at about 50°C. 6.19 g of this $TiCl_4$ EB complex was then charged into the
35 vibrating ball mill after the prior 24 hour co-comminution of the other materials, and the resulting mixture co-comminuted for an additional 20 hours at ambient temperature and under inert

atmosphere. This produced a solid catalyst component usable without requiring extraction or catalyst washing.

Another conventional catalyst was prepared, for comparison purposes with the catalysts of the present invention, approximately as follows: 30 g (0.315 mole) of MgCl_2 was co-comminuted with 5.22 g (0.0391 mole) AlCl_3 for 24 h in RBM under N_2 atmosphere. Then 4.02 g (0.0212 mole) of TiCl_4 was added. Ball milling was continued for another 24 h. 30 g yellow pro-catalyst powder was collected. It was calculated that the titanium component was about 2.6 weight percent, the aluminum component was about 2.7 weight percent, the magnesium component was about 19.3 weight percent, and the Mg:Al:Ti ratio was about 8:1:0.5.

15

EXAMPLES 3-19: Effect of Type I internal donors

A variety of pro-catalysts and catalysts were prepared to examine the effect of Type I internal donors on the effective surface area and catalyst activity:

20 Example 3: Same as Example 6 below, except using 1.18 g EtOBz. Calc'd: $\text{Ti}\ddagger=2.50$; $\text{EB/Mg}=0.025$ (mol/mol).

Example 4: MgCl_2 of 30 g, AlCl_3 of 5.25 g and EtOBz of 2.36 g (0.0158 mole) were ball milled (VBM) for 16 h, then TiCl_4 of 4.02 g was added and the mixture was ball milled for 25 another 16 h. Calc'n: $\text{Ti}\ddagger=2.43$; $\text{EB/Mg}=0.05$ (mol/mol).

Example 5: Same as Example 6, except using 4.72 g EtOBz. Calc'd: $\text{Ti}\ddagger=2.31$; $\text{EB/Mg}=0.10$ (mol/mol).

Example 6: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24 h, then 1.55 g (0.0131 mole) $(\text{EtO})\text{SiMe}_3$ and 30 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 7: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24 h, then 3.1 g (0.0263 mole) $(\text{EtO})\text{SiMe}_3$ and 4.02 g TiCl_4 were added. The mixture was ball milled for 35 another 24 h to give the pro-catalyst.

Example 8: 30 g MgCl₂ and 5.25 g AlCl₃ were ball milled (RBM) for 24 h, then 6.15 mL (0.0394 mole) (EtO)₃SiMe₃ and 4.02 g TiCl₄ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

5 Example 9: 30 g MgCl₂ and 5.25 g AlCl₃ were ball milled (RBM) for 24 h, then 2.47 g (0.0131 mole) C-donor and 4.02 g TiCl₄ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 10: 30 g MgCl₂ and 5.25 g AlCl₃ were ball
10 milled (RBM) for 24 h, then 7.42 g (0.0394 mole) C-donor and 4.02 g TiCl₄ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 11: 30 g MgCl₂ and 5.25 g AlCl₃ were ball milled (RBM) for 24 h, then 3.0 g (0.0131 mole) D-donor and 4.02
15 g TiCl₄ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 12: 30 g MgCl₂ and 5.25 g AlCl₃ were ball milled (RBM) for 24 h, then 9.0 g (0.0394 mole) D-donor and 4.02 g TiCl₄ were added. The mixture was ball milled for
20 another 24 h to give the pro-catalyst.

Example 13: 5 g of Example 2 was suspended in 100 mL toluene, stirred at 60°C for 1 h, filtered and suspended in 30 mL fresh toluene. 16.5 mL TiCl₄ and 0.74 mL (3.2 mmole) D-donor (Dicyclopentyldimethoxysilane) were added. Mixture was stirred
25 at 90°C for 1 h, filtered (solid dark brown), washed with heptane (turned to greenish yellow) and toluene (back to dark brown), again suspended in 30 mL toluene. 17 mL TiCl₄ was charged and mixture was stirred at 90°C for another 1 h. Solid filtered out and thoroughly washed with heptane.

30 Example 14: 1) MgCl₂, 30 g, AlCl₃, 5.25 g and (EtO)₃SiMe₃ 7.02 g (0.0394 mole) were ball milled for 24 h. 2) 5 g of above precursor was suspended in 100 mL toluene, stirred at 60°C for 1 h, filtered, solid washed with heptane, toluene and then suspended in 30 mL fresh toluene. 16.5 mL (150 mmole) TiCl₄ was
35 charged (slurry turned brown). The slurry was stirred at 90°C for 1 h, filtered, solid washed with heptane, toluene, then

again suspended in 30 mL toluene. 16.5 mL TiCl_4 was charged and reacted at 90°C for 1 h. The solid was washed with heptane. The solid was orange-red in toluene but turned to yellow after washed by heptane.

5 Example 15: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24 h, then 6.69 g (0.0394 mole) SiCl_4 and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

10 Example 16: 30 g MgCl_2 , 5.25 g AlCl_3 and 2.76 g dibutyl phthalate were co-ball milled for 24h, then 4.02 g TiCl_4 was added. The mixture was ball milled for another 24 h to provide the pro-catalyst.

15 Example 17: 30 g MgCl_2 and 2.76 g dibutyl phthalate were co-ball milled for 24h, then 4.02 g TiCl_4 was added. The mixture was ball milled for another 24 h to provide the pro-catalyst.

20 Example 18: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24h, then 7.68 g (0.0212 mole) diheptyl phthalate and 4.02 g (0.0212 mole) TiCl_4 were charged and ball milled for another 24 h.

Example 19: Same as Example 14 except without (EtO) $_2$ SiMe but with dropwise addition of 1.17 mL diheptyl phthalate (turned dark) before reacting at 90°C for 1 h.

25 These pro-catalysts were used in a catalyst for the polymerization of polypropylene to produce polymers having characteristics set forth in the Table below:

30

35

Example Number	Composition	Donor	Donor /Ti	Polymer. Run No	C.B. g/g-cat	ΔH_f J/g	m.p. °C	MFR g/10 min	MEK sol%
1	TiCl ₄ /MgCl ₂ /AlCl ₃ /EB/Anisole	EB & Anisole	nd	2507-39	11900	42.9	155.9	11	nd
2	TiCl ₄ /MgCl ₂ /AlCl ₃ (BM)	None	0	2536-1	16500	30	154	11	11
3	TiCl ₄ /MgCl ₂ /AlCl ₃ /EB (BM)	Ethyl Benzozole	0.37	2536-25	17600	31.8	153.8	10.3	12.5
4	TiCl ₄ /MgCl ₂ /AlCl ₃ /EB (BM)	Ethyl Benzozole	0.74	2536-21	18500	35.1	154.5	9.6	11.1
5	TiCl ₄ /MgCl ₂ /AlCl ₃ /EB (BM)	Ethyl Benzozole	1.48	2536-27	13800	39.2	154.7	7.4	12.2
6	TiCl ₄ /MgCl ₂ /AlCl ₃ /EB (BM)	(EtO)Si Me ₃	0.62	2540-31	18800	36.1	153.9	8.4	10.4
7	TiCl ₄ /MgCl ₂ /AlCl ₃ /EB (BM)	(EtO)Si Me ₃	1.24	2536-99	23100	39.6	153.5	8.9	7.6
8	TiCl ₄ /MgCl ₂ /AlCl ₃ /EB (BM)	(EtO)Si Me ₃	1.86	2536-97	21000	43.9	152.4	15.3	7.8
9	TiCl ₄ /MgCl ₂ /AlCl ₃ /C-donor (BM)	C-donor	0.62	2540-7	19400	33.7	153.1	8.6	7.8
10	TiCl ₄ /MgCl ₂ /AlCl ₃ /C-donor (BM)	C-donor	1.86	2536-95	13400	40.9	152.8	7.5	5.5

(Continued)

Example Number	Composition	Donor	Donor/PI	Polym. Run No	C.E. g/g-est	ΔH_f J/g	m.p. °C	MFR g/10 min	MEK sol%
11	TiCl ₄ /MgCl ₂ /AlCl ₃ /D-donor (BM)	D-donor	0.62	2540-6	19000	35.9	153.7	9.9	5.7
12	TiCl ₄ /MgCl ₂ /AlCl ₃ /D-donor (BM)	D-donor	1.86	2536-93	13800	36.9	154.4	3.6	4.7
13	TiCl ₄ /MgCl ₂ /AlCl ₃ /D-donor (Solution)	D-donor	nd	2536-62	27300	37.7	154.2	12.7	9.4
14	TiCl ₄ /MgCl ₂ /AlCl ₃ / (BO) ₂ SiMe ₃ (Solution)	(BO) ₂ SiMe ₃	nd	2536-34	18200	31.1	155.2	4.6	7.9
15	TiCl ₄ /MgCl ₂ /AlCl ₃ /SiCl ₄ (BM)	SiCl ₄	1.86	2536-91	17500	34.2	153.6	13.7	7.1
16	TiCl ₄ /MgCl ₂ /AlCl ₃ /DBP (BM)	Dibutyl Phthalate	0.47	2541-59	13900	46.9	156.0	4.2	8.4
17	TiCl ₄ /MgCl ₂ /DBP (BM)	Dibutyl Phthalate	0.47	2541-62	9900	44.2	155.4	4.0	6.8
18	TiCl ₄ /MgCl ₂ /AlCl ₃ /DHP (BM)	Dibutyl Phthalate	1	2536-38	10700	49.7	156.1	0.75	4.5
19	TiCl ₄ /MgCl ₂ /AlCl ₃ /DHP (Solution)	Dibutyl Phthalate	nd	2536-36	9700	49.7	156.7	1.2	7.1

nd = not determined
 Polymerization conditions: 10 mg catalyst; 300 g propylene; $\Delta T/PI = 200$; 60°C for 1 hour.

Examples 3-19 illustrate a variety of Type I donors and their effects on polymer properties. They were typically co-milled with catalyst supports ($\text{MgCl}_2/\text{AlCl}_3$) prior to TiCl_4 addition, except for the catalysts made by a solution process.

5 The effect of the donors produced by the ball-mill method on productivity indicates silane donors are more effective than other donors in enhancing the productivity at low dosages. Those donors prepared by the solution process indicate a productivity enhancement that, with increasing donor dosage,

10 also indicates an increased heat of fusion of the polymer. The desired donors are those that yield the maximum productivity increase while causing the minimum change to the heat of fusion. Silane donors advantageously meet the criteria most effectively.

15 EXAMPLES 20-31: Effect of Type II Internal Donors

A variety of these catalysts were examined for Type II internal donor characteristics in an attempt to locate a catalyst that produces a smaller amount of the low molecular weight FPO polymers than typical.

20 Example 20: See Example 2.

Example 21: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24 h, then 4.46 g (0.0394 mole) cis 2,6-dimethylpiperidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

25 Example 22: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24 h, then 5.56 g (0.0393 mole) 2,2,6,6-tetramethylpiperidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

30 Example 23: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24 h, then 4.19 mL (0.0394 mole) 2,5-dimethylfuran and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

35 Example 24: 30 g MgCl_2 and 5.25 g AlCl_3 were ball milled (RBM) for 24 h, then 3.95 g (0.0394 mole) 2,5-dimethyltetrahydrofuran and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 25: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 3.67 g (0.0394 mol) 2-picoline and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

5 Example 26: 21.4 g $MgCl_2$ and 3.75 g $AlCl_3$ were ball milled (RBM) for 24 h, then 5.0 g (0.0281 mole) 4-chloroquinoline and 2.85 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

10 Example 27: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 4.59 mL (0.0394 mole) 2,6-Lutidine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

15 Example 28: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 4.77 g (0.0393 mole) 2,4,6-collidine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

20 Example 29: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 5.0 g (0.0394 mole) 6-chloro-2-picoline and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 30: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 5.83 g (0.0393 mole) 2,6-dichloropyridine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

25 Example 31: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 9.33 g (0.0394 mol) 2,6-dibromopyridine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

30 These catalysts were used in the polymerization of polypropylene to produce polymers having characteristics set forth in the Table below:

35

Example No.	Donor	Polym. Run No.	C.R. g/g-ent.Δ	ΔH _f J/g	M.P. °C	MFR g/10 min	MEK Sol%	M _n x10 ⁻³	M _w x10 ⁻³	PDI
20	None	2536-1	16500	30	154	11	11	21	209	9.9
21	2,6-dimethylpiperidine	2536-79	7900	35.9	154.3	4.0	6.0	28	239	8.47
22	2,2,6,6-Tetramethylpiperidine	2540-51	7400	51.1	156.4	0.68	5.9	33	385	12.2
23	2,5-dimethylfuran	2536-76	14000	35.1	154.1	6.4	8.4	27	277	9.6
24	2,5-dimethyl-tetrahydrofuran	2536-40	14700	28.4	153.6	18.4	9.2	20	201	9.9
25	2-picoline	2540-44	13700	27.8	153.6	7.3	11.0	22	214	9.7
26	4-chloroquinoline	2536-46	6500	30.2	154.4	3.6	7.6	25	239	9.4

(Continued)

Example No. ^a	Donor	Polym Run No ^b	C.B. g/g-eth.h	ΔH_f J/g	M.P. °C	MFR g/10 min	MEK Sol%	$M_n \times 10^{-3}$	$M_w \times 10^{-3}$	PDI
27	2,6-Lutidine	2536-68	6800	27.5	155.0	1.4	4.8	36	283	7.8
28	2,4,6-collidine	2540-37	9000	29.7	154.7	1.22	4.62			
29	6-chloro-2-picoline	2536-83	9300	27.5	154.5	1.2	3.8	36	280	7.8
30	2,6-dichloropyridine	2540-35	9100	26.9	154.4	3.1	8.1	32	265	8.29
31	2,6-dibromopyridine	2540-86	9300	27.6	153.6	2.1	8.9	29	295	10.3

^a - Catalyst general composition: $TiCl_4/MgCl_2/AlCl_3/Donor$, ball milled, Donor/Ti = 1.86.

^b - Polymerization conditions: 10 mg catalyst; $Al/Ti = 200$; $60^\circ C$ for 1 h.

Examples 20-31 illustrate a variety of Type II donors, including aromatic, sterically hindered nitrogen-based Lewis base donors. It was desired to obtain a higher molecular weight indicated by a lower MFR, while having a minimal effect on crystallinity. The results above suggest that: (1) the nitrogen-based donors are generally more effective in increasing molecular weight than oxygen-based donors (Examples 23 and 24, for example); (2) non-aromatic nitrogen-based Lewis bases, e.g., Examples 21 and 22, had a more pronounced effect on polymer heat of fusion than the aromatic derivatives, the latter being weaker Lewis bases; and (3) the steric hindrance around the nitrogen atom importantly appears to increase steric hindrance from 2-picoline to 2,6-lutidine to 2,6-dibromopyridine, with the low molecular weight fractions first decreased, then increased again. 2,6-lutidine and 6-chloro-2-picoline were more effective in reducing the LMW fractions.

EXAMPLES 32-44: Combinations of Type I and Type II Donors

A variety of catalysts were prepared and tested to obtain a good productivity, while yielding higher molecular weight and lower crystallinity:

Example 32: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 5 h, 1.55 g (0.0131 mole) $(EtO)SiMe_3$ was added and ball milled for 19 h, then 4.22 g (0.0394 mole) 2,6-lutidine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 33: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 hrs., then 3.1 g (0.026 mole) $(EtO)SiMe_3$ and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 hrs. 10 g of this mixture were suspended in 30 mL toluene, to which 33 mL $TiCl_4$ and 0.75 mL (0.0064 mole) 2,6-lutidine were added. The mixture was stirred at 90°C for 1 h, then filtered (filtrate orange) and washed with heptane for 3 times to give the yellow pro-catalyst.

Example 34: 30 g $MgCl_2$, 5.25 g $AlCl_3$, and 0.74 g diethoxydimethylsilane were co-ball milled for 24 h, then 1.41

g 2,6-Lutidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 35: 30 g MgCl_2 , 5.25 g AlCl_3 and 0.95 g C-donor were ball milled (RBM) for 24 h, then 1.41 g (0.0131 mol) 2,6-Lutidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 36: 30 g MgCl_2 , 5.25 g AlCl_3 and 1.23 g dicyclopentyldimethoxysilane were ball milled for 24 h, then 1.41 g 2,6-Lutidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 37: 30 g MgCl_2 , 5.25 g AlCl_3 and 1.38 dibutyl phthalate were ball milled for 24 h, then 1.41 g 2,6-lutidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 38: 30 g MgCl_2 , 5.25 g AlCl_3 and 0.95 g C-donor were ball milled (RBM) for 24 h, then 1.66 g (0.0131 mol) 6-chloro-2-picoline and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 39: 30 g MgCl_2 , 5.25 g AlCl_3 and 0.95 g C-donor were ball milled (RBM) for 24 h, then 3.32 g (0.0262 mol) 6-chloro-2-picoline and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 40: 5 g of the pro-catalyst in Example 2 was suspended in 100 mL toluene and stirred at 60°C for 1 h. The solid was filtered out and re-suspended in 30 mL toluene. 16.5 mL TiCl_4 and 0.1 mL (0.0005 mole) C-donor were added into the suspension. The mixture was then stirred at 90°C for 1 h, filtered and washed with heptane then toluene. The solid was re-suspended in 30 mL toluene and mixed with 16.5 mL TiCl_4 and 0.41 g (0.0032 mole) 6-chloro-2-picoline. The mixture was brought to reaction at 90° for another hour, then filtered and washed with heptane for 3 times to give the pro-catalyst.

Example 41: 5 g of the pro-catalyst in Example 2 was suspended in 100 mL toluene and stirred at 60°C for 1 h. The solid was filtered out and re-suspended in 30 mL toluene. 16.5 mL TiCl_4 and 0.25 mL (0.001 mole) D-donor were added into the

suspension. The mixture was then stirred at 90°C for 1 h, filtered and washed with heptane twice. The solid was re-suspended in 30 mL toluene and mixed with 16.5 mL TiCl₄ and 0.41 g (0.0032 mole) 6-chloro-2-picoline. The mixture was brought to reaction at 90° for another hour, then filtered and washed with heptane for 3 times to give the pro-catalyst.

Example 42: 5 g of the pro-catalyst in Example 2 was suspended in 100 mL toluene and stirred at 60°C for 1 h. The solid was filtered out and re-suspended in 30 mL toluene. 16.5 mL TiCl₄ and 0.1 mL (0.0004 mole) D-donor were added into the suspension. The mixture was then stirred at 90°C for 1 h, filtered and washed with heptane then toluene. The solid was re-suspended in 30 mL toluene and mixed with 16.5 mL TiCl₄ and 0.41 g (0.0032 mole) 6-chloro-2-picoline. The mixture was brought to reaction at 90° for another hour, then filtered and washed with heptane for 3 times to give the pro-catalyst.

Example 43: 30 mg MgCl₂ and 5.25 g AlCl₃ were ball milled (RBM) for 24 hrs., then 1.55 g (0.013 mole) (EtO)SiMe₃ and 4.02 g TiCl₄ were added. The mixture was ball milled for another 24 hrs. 5 g of this mixture was suspended in 100 mL toluene and stirred at 80°C for 1 h. The solid was filtered out and re-suspended in 30 mL toluene. 16.5 mL TiCl₄ and 0.41 g (0.0032 mole) 6-chloro-2-picoline were added into the suspension. The mixture was then stirred at 90°C for 1 h, filtered and washed with heptane for three times to give the pro-catalyst.

Example 44: 5 g of the mixture of Example 43 was suspended in 100 mL toluene and stirred at 80°C for 1 h. The solid was filtered out and re-suspended in 30 mL toluene. 16.5 mL TiCl₄ and 0.0032 mole 2,6-dichloropyridine (dissolved in toluene) were added into the suspension. The mixture was then stirred at 90°C for 1 h, filtered and washed with heptane for three times to give the pro-catalyst.

These pro-catalysts were used in catalysts for the polymerization of polypropylene to produce polymers having characteristics set forth in the Table below:

Example Number	A-type Donor (Donor/IT)	B-type Donor (Donor/IT)	Polym. Rem No	C.E. g/g-soln	ΔH_f J/g	M.P. °C	MFR g/10 min	MEK Sol %
32 (RM)	(BO)SDM63 SI/IT=0.62	2,6-Lutidine N/IT=1.86	2540-24	4500	36.8	153.5	1.2	7.1
33 (solution)	(BO)SDM63 SI/IT nd	2,6-Lutidine N/IT nd	2540-39	10900	42.6	153.3	1.3	4.4
34 (RM)	(BO)SDM62 SI/IT=0.23	2,6-Lutidine N/IT=0.62	2541-53	14300	36.6	154.2	1.9	7.2
35 (RM)	C-donor SI/IT=0.23	2,6-Lutidine N/IT=0.62	2540-91	15500	28.3	152.9	1.6	8.0
36 (RM)	D-donor SI/IT=0.23	2,6-Lutidine N/IT=0.62	2541-51	14000	38.3	154.5	1.3	5.3
37 (RM)	Dibutyl phthalate DBP/IT=0.23	2,6-Lutidine N/IT=0.62	2541-23	10500	32.9	154.5	nd	7.4
38 (RM)	C-donor SI/IT=0.23	6-chloro-2-picoline N/IT=0.62	2540-96	14700	29.6	153.7	3.1	7.4

(cont'd)

Example No.	A-type Donor (Donor/TI)	B-type Donor (Donor/TI)	Polym. Run No	C.R. g/sec-h	ΔH _f J/g	M.P. °C	MFR g/10 min	MEK Sol%
39 (BM)	C-donor S/TI=0.23	6-chloro-2-picoline N/TI=1.24	2540-98	10500	27.8	153.8	1.2	7.0
40 (solution)	C-donor S/TI n.d.	6-chloro-2-picoline N/TI n.d.	2540-77	9300	26.7	154.1	1.0	6.5
41 (solution)	D-donor S/TI n.d.	6-chloro-2-picoline N/TI n.d.	2540-53	15700	29.7	153.3	1.8	5.7
42 (solution)	D-donor S/TI n.d.	6-chloro-2-picoline N/TI n.d.	2540-67	9700	28.1	155.0	1.7	5.7
43 (solution)	(BO)SDMA3 S/TI n.d.	6-chloro-2-picoline N/TI n.d.	2540-47	8300	35.7	155.4	1.0	6.8
44 (solution)	(BO)SDMA3 S/TI n.d.	2,6-dichloropyridine N/TI n.d.	2540-49	19100	36.1	154.1	4.2	6.9

BM = ball milling

The goal of Examples 32-44 was to obtain a catalyst with good productivity, while yielding higher molecular weight and lower crystallinity. Examples 32-44 illustrate the combinations of these donors by both ball mill and solution process. It appeared that the most promising combinations are those between C-donor, D-donor and 2,6-Lutidine, 6-chloro-2-picoline. D-donor and 2,6-Lutidine seemed to cause slightly higher heat of fusion. Also, the solution process appeared less advantageous as compared to the ball mill process.

10

EXAMPLES 45-53: Optimization of Catalyst Formulation With C-donor (Type I) and 2,6-Lutidine (Type II)

Likely candidates for catalysts having all desired properties were selected to optimize all characteristics in the catalyst and resulting FPO polymer:

15

Example 45: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 4.59 mL (0.0394 mole) 2,6-Lutidine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

20

Example 46: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 2.81 g (0.0262 mol) 2,6-Lutidine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

25

Example 47: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 1.41 g (0.0131 mol) 2,6-Lutidine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

30

Example 48: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 0.74 g (0.0069 mol) 2,6-Lutidine and 4.02 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

35

Example 49: 30 g $MgCl_2$ and 5.25 g $AlCl_3$ were ball milled (RBM) for 24 h, then 1.41 g (0.0131 mol) 2,6-Lutidine and 8.04 g $TiCl_4$ were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 50: 30 g $MgCl_2$, 5.25 g $AlCl_3$ and 0.95 g C-donor were ball milled (RBM) for 24 h, then 1.41 g (0.0131 mol)

2,6-Lutidine and 8.04 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 51: 30 g MgCl_2 , 5.25 g AlCl_3 and 0.48 g C-donor were ball milled (RBM) for 24 h, then 1.41 g (0.0131 mol) 2,6-Lutidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 52: 30 g MgCl_2 , 5.25 g AlCl_3 and 0.95 g C-donor were ball milled (RBM) for 24 h, then 1.41 g (0.0131 mol) 2,6-Lutidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

Example 53: 30 g MgCl_2 , 5.25 g AlCl_3 and 1.43 g C-donor were ball milled (RBM) for 24 h, then 1.41 g (0.0131 mol) 2,6-Lutidine and 4.02 g TiCl_4 were added. The mixture was ball milled for another 24 h to give the pro-catalyst.

These pro-catalysts were used in catalysts for the polymerization of polypropylene to produce polymers having characteristics set forth in the Table below:

20

25

30

35

Example No.	Ti %	C-donor (Si/Ti)	2,6-Lutidine (N/Ti)	Polymn. Run No	C.E. g/g-cat.h	ΔH_f J/g	M.P. °C	MFR g/10 min	MEK Sol%	$M_n \times 10^{-3}$	$M_w \times 10^{-3}$	PDI
45	2.33	0	1.86	2540-1	6400	31.8	154.8	1.5	6.8	36	283	7.78
46	2.41	0	1.24	2540-71	8800	27.4	154.2	1.6	7.2	40	299	7.45
47	2.50	0	0.62	2540-75	12700	27.3	153.4	1.9	6.9	32	273	8.4
48	2.54	0	0.32	2540-82	15900	29.5	152.6	3.2	10.1	26	247	9.41
49	4.54	0	0.31	2540-80	12600	32.7	154.6	1.9	6.6	31	242	7.74
50	4.47	0.118	0.31	2540-89	15100	38.8	154.0	2.4	5.5	36	263	7.37
51	2.47	0.118	0.62	2541-6	14300	29.5	153.6	2.3	8.0			
52	2.44	0.23	0.62	2540-91	15500	28.3	152.9	1.6	8.0	32	274	8.48
53	2.41	0.35	0.62	2541-8	15000	37.1	153.5	1.8	5.9			

Examples 45-53 illustrate the optimization of donor dosage by locating a point where the MFR is sufficiently low, but catalyst productivity is acceptably high for polymerization, as well as the optimization of maintaining improved productivity while obtaining low heat of fusion. Example 52 appears as the pro-catalyst advantageously having the optimum recipe, with a relatively high productivity of 15,500 g/ g catalyst, relatively low H_f of about 28.3 J/g, and significantly lower MFR of about 1.6 g / 10 min. than for other catalyst formulations.

10

EXAMPLE 54: METHOD FOR PREPARATION OF A PREFERRED CATALYST

120 lbs. of solid magnesium chloride ("MgCl₂") and 21 lbs. of solid aluminum chloride ("AlCl₃") were charged to a 250 L vibratory ball mill and mixed for about 15 minutes. Then, 3.8 lbs. of cyclohexylmethyldimethoxysilane was sprayed into the stainless steel container. Alternatively, the silane could have been added with the other two components before ball milling. The mixture was then ball milled for 16 hours at room temperature.

20

Subsequent to the initial ball milling, 3.7 lbs. of liquid 2,6-lutidine and 16.1 lbs. of liquid titanium tetrachloride (TiCl₄) were added to the mixture. An alternative heterocyclic aromatic amine, such as about 4.5 lbs. of liquid 6-chloro-2-picoline could instead have been substituted. The lutidine was directly added to these components, although spray addition of the two liquid components into the existing mixture over about two to three hours would also be suitable. The five (5) components were then ball milled for about an additional 16 hours. The ball milling involves vibrating steel balls to pound the component particles, imparting heat to the ball milling vessel; however, the vessel was temperature controlled to maintain approximately room temperature during the ball milling.

In the preparation of a variety of FPO polymers, the productivity of the present catalyst has ranged from about a 30 to 55 percent increase, compared to conventional catalysts.

EXAMPLES 55-62: Pilot Plant Continuous Process

Polymers were prepared in a large scale continuous pilot plant operation, wherein monomers, hydrogen, and catalyst components were separately and continuously charged to a stirred reactor. The total monomer feed rate corresponded to about a 1.8 hour residence time in the reactor. Triethylaluminum ("TEA") and external modifier cyclohexylmethyldimethoxysilane ("CMDS") were pumped into the reactor as about 5 weight percent and 0.25 weight percent heptane solutions, respectively. The solid catalyst component had a titanium content of about 2.2 weight percent and was prepared according to Example 54. The solid catalyst component was pumped into the reactor as a 25 weight percent mixture in petrolatum. The catalyst components were added at rates directly proportional to the polymer production rates, and in amounts sufficient to maintain the polymer solids concentration in the reactor slurry at values typically in the range of about 30 to 50 weight percent. The catalyst productivity (lbs polymer/lb solid catalyst) was calculated from the polymer solids withdrawal rate and the solid catalyst component addition rate. The product polymers were separated from unreacted monomers, deactivated, stabilized, and pelletized, followed by testing to determine polymer characteristics. The Table below summarizes the pertinent operating conditions and results of the physical testing of the polymer characteristics.

30

35

	Example	55	56	57	58	59	60	61	62
	Reactor Temp °F	135	135	135	135	135	135	140	140
	Propylene (lbs/hr)	138	154	136	146	142	147	147	135
5	Ethylene (lbs/hr)	-	-	1.5	1.1	-	-	-	-
	Hydrogen (lbs/hr)	-	0.028	-	0.028	0.026	0.040	0.027	0.04
	Solid catalyst (lbs/hr)	0.0045	0.0038	0.0029	0.0026	0.0045	0.0048	0.0055	0.0046
	Al/Ti mol ratio	162	210	256	364	155	184	161	191
10	CMDS/Ti mol ratio	-	-	-	-	0.77	0.87	2	2
	Productivity (lbs/hr)	9880	11600	16110	16890	9630	10420	8480	10090
	Ethylene - wt %	-	-	2.2	2.6	-	-	-	-
	ΔH_f (J/g)	26.6	23.8	17.8	18.2	33.5	36.1	50.4	53.4
15	MFR (g / 10 min)	4.6	13.6	4.9	15.8	7.4	30	4.8	25.9
	Tensile Modulus (kpsi)	11	9	5	3	20	20	40	43
	Tensile stress @ 311% strain - psi	1330	935	983	660	1400	1087	2100	1720
	% Tensile set, 0/24 hr	36/23	34/19	31/17	30/17	46/31	45/29	63/45	69/50
20	VICAT softening (°C)	58	46	41	42	66	57	95	97
	Shore D Hardness	46	45	38	34	51	50	61	62

25 EXAMPLES 63-71: Preparation of Various Polymers

The polymerization of several polymers, which are by no means indicative of the broad scope of polymers this invention is meant to encompass, was examined using the ball-milled catalyst of the present invention. The characteristics of some of these polymers are set forth below:

Example No.	63	64	65	66	67	68	69	70	71
Pro-cat., mg	10	10	10	10	10	10	10	10	10
Co-catalyst	TEA	TEA	TEA	TEA	TEA	TEA	TEA	TEA	TEA
Al/Ti, mol/mol	200	200	200	200	200	200	200	200	200
Modifier	CMDS								
Modifier/Ti, mol/mol	1								
H ₂ , psig	0	0	5	5	0	0	0	0	0
Ethylene, g/min ^{a)}	0	0	0	0	0.27	0	0	0	0
10 Propylene, mL	660	660	660	660	660	610	460	610	460
1-butene, mL	0	0	0	0	0	50	200	0	0
1-pentene, mL	0	0	0	0	0	0	0	50	200
C.E. g/g cat/h	15300	10400	17500	13100	19600	11000	10600	9400	8000
H.F., J/g	32.2	57.2	34.8	62.7	25.6	21.8	13.8	21.9	6.6
15 m.p., °C	153.7	156.4	155.9	158.3	146.7	137.3	109.7	141.0	126.9
MFR, g/10 min	2.16	0.3	12.0	21.9	2.24	4.1	6.3	4.4	10.2

Batch polymerization in 1 liter autoclave, 60°C, for 1 hr.

20 a) Ethylene continuously fed during 1 hour reaction time.

EXAMPLES 72-83: Preparation of Various Copolymers

Each of the polymer products in Examples 72 to 83 set forth in the Table below were prepared in general by the process described in the Examples above. Initially, a clean one-Liter stainless steel autoclave reactor equipped with an agitator was purged with nitrogen to remove impurities. Next, triethylaluminum is added to the reactor in sufficient quantity to provide an Al:Ti atomic ratio of about 200:1 when followed by addition of a mineral oil suspension containing about 10 mg of solid procatalyst as described herein. The mixed monomer charges, which include 660 mL liquid volume, were subsequently introduced into the reactor at an effective pressure and under thermal control to maintain a reaction temperature of 60°C for one hour. The "C" and "D" donors were those used previously. After one hour, the unreacted monomer was vented off and the polymer product was recovered using conventional techniques. The characteristics of some of these polymer products are set forth below:

20

25

30

35

Example No.	72	73	74	75	76	77	78	79	80	81	82	83
Propylene, mL	640	610	560	460	640	610	560	460	640	610	560	460
1-butene, mL	20	50	100	200	0	0	0	0	0	0	0	0
5 1-pentene, mL	0	0	0	0	20	50	100	200	0	0	0	0
1-octene, mL	0	0	0	0	0	0	0	0	20	50	100	200
C.E. g/g-cat/h	13200	11000	10600	10700	13000	10400	10300	8000	12600	12200	12300	11100
wt% C ₄ ^a	1.8	5.9	11.4	28.7	3.5	4.2	8.9	26.4	1.2	3.0	8.5	13.8
DC ₃ ^b	69.7	21.8	11.3	4.6	65.7	39.8	19.5	8.0	186.2	84.7	32.7	17.4
10 DC ₄ ^c	-	1.1	1.1	1.4	-	-	1.1	1.6	-	-	-	1.1
H.F., J/g	28.3	25.4	18.3	7.4	23.9	18.4	16.9	10.4	26.2	24.0	19.9	14.3
m.p., °C	149.0	136.6	131.6	110.1	146.5	139.9	132.5	130.0	150.5	147.2	144.2	144.4
T _g , °C	-1.5	-3.0	-5.1	-9.8	-2.1	-3.4	-3.9	-6.8	-2.8	-3.0	-5.6	-11.9
MFR, g/10 min	3.2	4.0	2.8	6.6	3.8	5.0	6.8	10.2	2.9	3.8	5.3	8.9
Density, g/cm ³	0.873	0.865	0.869	0.864	0.871	0.868	0.866	0.856	0.87	0.874	0.866	0.863
MEK sol ^a	8.1	6.8	5.2	4.6	8.0	7.2	8.2	6.1	7.6	8.1	7.4	7.1

Batch polymerization in 1 liter autoclave. Catalyst 10 mg; TEA/Ti 200; Total liquid monomer charge 660 mL; 60°C; 1 hr.

a) Weight percentage of co-monomer incorporation.

b) Number average sequence length for propylene units.

c) Number average sequence length for co-monomer units.

EXAMPLES 84-99: ETHYLENE CO-MONOMER POLYMERS

The following examples illustrate various types of polymers produced according to the present invention by using ethylene and at least one other co-monomer as a monomeric raw material. These particular polymers used propylene as the other co-monomer in the monomeric raw material with ethylene.

10

15

20

25

30

35

HIGHER ETHYLENE FPO PRODUCTS

EXAMPLE NO.	84	85	86	87	88	89	90	91	92	93
LOT Melt Flow, g/10min@230°C	5.3	5	5.8	5.7	5.5	5.3	4.7	5	5.5	5.2
Ethylene Content, wt%	2.2	3.8	5.7	7.3	9.7	9.6	14.8	17.7	15	16.6
DSC M_p/T_g (°C)	147.2/93.8	144.5/92.2	136.6/88.1	132.0/85.3	127.6/84.4	127.9/84.5	123.3/80.9	118.9/77.6	120.5/77.7	114.9/75
Enthalpy (J/g)	17.5/21.6	14/-19.7	14.1/-13.1	11.5/-12.6	7.9/-10.6	8.1/-9.6	5.7/-7.7	4/-4.4	5.2/-6.8	4.3/-4.9
Density, g/cm ³	-	-	0.8683	-	-	0.8597	-	0.8446	-	-
DSC T_g , °C	-	-6.7	-9.3	-16.2	-	-17.7	-24.1	-26.1	-	-
MEK Solubles, wt%	9.03	9.42	7.89	7.67	7.07	6.77	6.8	7.2	-	-
Diethyl Ether Sol., wt.	31.5	35.9	41.5	45.2	47	45.5	48.2	47.4	-	-
Hexane Sol. wt%	39.5	45.6	51.8	62.6	70.5	68.6	77.3	81.6	80.6	82.3
Shore Hardness, A/D scales	377-	337-	28/85	25/81	20/75	20/76	15/67	12/61	15/66	12/62
Shrinkage Test:										
Length (in/in)	-	0.0363	-	-	-	0.0669		0.0838	-	-
Width (in/in)	-	0.0016	-	-	-	-0.0078		-0.0065	-	-
Molecular Weight Measures:										
GPC M_n (x1000)	27	26	27	27	27	27	27	28	32	27
M_w (x1000)	219	221	222	224	222	226	218	207	219	203
M_z (x1000)	792	836	873	889	905	916	968	850	857	821
PDI	8.1	8.5	8.22	8.3	8.22	8.4	8.1	7.4	6.8	7.5

5

10

15

20

25

- 47 -

EXAMPLE NO.	84	85	86	87	88	89	90	91	92	93
I.V. of neat polymer, dl/g	1.48	1.96	1.24	1.63	1.25	1.67	1.37	1.23	—	—
I.V. of ether soluble fraction, dl/g	0.826	0.87	0.61	0.82	0.87	0.79	0.9	0.91	—	—
Cast Film 1 mil by 6 inches:										
Measured Thickness (mil)	1.6-2.1	—	1.6-1.7	—	—	1.3	—	1.7-1.8	—	—
Machine Direction:										
Stress @ Yield (psi)	733	—	NY	—	—	NY	—	NY	—	—
Stress @ Break (psi)	1761	—	1468	—	—	1052	—	870	—	—
Strain @ Break (%)	549	—	568	—	—	415	—	656	—	—
Transverse Direction:										
Stress @ Yield (psi)	539	—	401	—	—	NY	—	NY	—	—
Stress @ Break (psi)	NB(989)	—	NB(728)	—	—	NB(516)	—	NB(226)	—	—
Strain @ Break (%)	NB(>700)	—	NB(>700)	—	—	NB(>700)	—	NB(>700)	—	—
Tensile Modulus (kpsi)	5.1	3.8	2.6	2.2	1.6	1.6	1.2	0.87	1.11	0.88
Tensile Strain at Yield (%)	NY	NY	NY	NY	NY	NY	NY	NY	NY	NY
Tensile Strain at Break (%)	NY	NY	NY	NY	NY	NY	NY	NY	NY	NY
Tensile Strain at Break (%)	NB	NB	NB	NB	NB	NB	NB	NB	NB	NB
Tensile Strain at Break (psi)	NB	NB	NB	NB	NB	NB	NB	NB	NB	NB
Tensile Strain at Max. Strain (311%) (psi)	936	844	699	626	550	547	359	270	354	291
Tensile Set after 300% Extension (%) (0/24h)	31/16	30/17	30/15	29/15	29/13	29/13	35/13	38/13	36/14	36/13

EXAMPLE NO.	84	85	86	87	88	89	90	91	92	93
VICAT Softening Temperature (°C)	40	40	40	39	43	43	23	23	23	23
Melt Swell Ratio (210°C/5 kg)	1.502	1.52	1.55	1.566	1.524	1.536	1.486	1.49	1.498	1.46
Zero-Shear Viscosity (Pa·s)	9675	8823	8312	8796	8456	8624	8713	7945	7984	7740
Crossover Modulus (Pa)	22044	22277	22461	22800	24509	24638	29304	31881	29641	30232
PDI = 100,000/Go	4.54	4.49	4.45	4.38	4.08	4.06	3.41	3.14	3.37	3.31
Crossover Frequency, rad/s	21.09	23.2	25.6	25.13	27.75	27.99	34.04	40.21	37.17	39.79

5

10

15

20

25

HIGHER ETHYLENE FFO PRODUCTS WITH DONOR ADDED

EXAMPLE NO.	94	95	96	97	98	99
LOT Melt Flow, g / 10 min. @ 230°C	5.5	8.4	4	4.8	5.6	6.9
Ethylene Content, wt%	9.7	6.2	14.7	12.6	9.8	9.8
DSC M_f/F_g (°C)	132.2/86.6	136.3/93/1	121.9/81.1	126/84.6	130.8/88.8	130.8/87.5
Enthalpy (J/g)	27.3/-30.7	23/-24.7	14.6/-19.4	17.8/20.3	21/-18.9	29.4/-30.7
Density, g/cm ³	—	—	—	—	0.874	0.878
MEK Solubles, wt%	4.96	6.31	3.4	—	—	—
Diethyl Ether Sol., wt%	23	27.7	29.5	—	—	—
Shrinkage Test:						
Length (in/in)	—	0.0125	0.0181	—	0.0131	0.0125
Width (in/in)	—	0.0137	0.0143	—	0.0133	0.0136
I.V. of neat polymer, dl/g	1.9	1.3	1.65	—	—	—
I.V. of ether soluble fraction, dl/g	0.57	0.37	0.8	—	—	—
Cast Film 1 mil by 6 inches:						
Measured Thickness (mil)	1.4-1.5	1.4-1.7	1.4-1.5	—	—	—
Machine Direction			711	—	—	—
Stress @ Yield (psi)	1047	959	1356	—	—	—
Stress @ Break (psi)	2760	2043	552	—	—	—

EXAMPLE NO.	94	95	96	97	98	99
Strain @ Break(%)	538	653	-	-	-	-
Transverse Direction						
Stress @ Yield(psi)	733	774	566	-	-	-
Stress @ Break(psi)	NB(1500)	NB(1510)	NB(1190)	-	-	-
Strain @ Break(%)	NB	NB	NB	-	-	-

5

10

15

20

25

Although preferred embodiments of the invention have been described in the foregoing description, it will be understood that the invention is not limited to the specific embodiments disclosed
5 herein but is capable of numerous modifications by one of ordinary skill in the art. It will be understood that the materials used and the chemical details may be slightly different or modified without departing from the methods and compositions disclosed and taught by the present invention.

10

15

20

25

30

35

THE CLAIMS

What is claimed is:

1. A method of preparing polyolefin polymers comprising
5 polymerizing an α -olefin monomeric raw material in the presence
of a catalyst comprising:
a pro-catalyst comprising:
a magnesium halide,
an aluminum halide,
10 a tetravalent titanium halide,
an electron donor; and
a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, wherein R_1
and R_2 are each an H, C_{1-6} alkyl, aryl, C_{5-12} cycloalkyl, each of
which may be unsubstituted, mono- or di-substituted, and R_3 and
 R_4 are H,
15 C_{1-6} alkyl, or a mono- or di-substituted C_{1-6} alkyl;
and
a co-catalyst comprising an organometallic compound, or
reaction products of the pro-catalyst and the co-catalyst,
wherein the electron donor is present in an amount sufficient
20 to reduce the stickiness of the resultant flexible polyolefin
polymers.
2. The method of claim 1, which further comprises
selecting the monomeric raw material to be a plurality of
25 alpha-olefin monomers.
3. The method of claim 2, which further comprises
selecting the plurality of alpha-olefin monomers to be monomers
of propylene, ethylene, butene, pentene, octene, or mixtures
thereof.
30
4. The method of claim 2, which further comprises
selecting the plurality of alpha-olefin monomers to be

propylene and at least one additional monomer having between about 2 to 12 carbon atoms per molecule.

5 5. The method of claim 4, wherein the additional monomer is selected to be at least one of ethylene, 1-butene, 1-pentene or 1-octene.

10 6. The method of claim 3, which further comprises providing ethylene in the monomeric raw material in an amount of about 1 to 40 weight percent.

7. The method of claim 6, which further comprises providing ethylene in the monomeric raw material in an amount of about 1 to 20 weight percent.

15 8. The method of claim 1, which further comprises adding hydrogen to the polymerization in an amount of less than about 10 weight percent.

20 9. The method of claim 1, which further comprises selecting the organometallic compound to be a metal alkane.

10. The method of claim 9, which further comprises selecting the organometallic compound to be an aluminum alkane.

25 11. The method of claim 1, which further comprises adding external modifier to the catalyst in an amount sufficient to increase the crystallinity of the polyolefin polymers to a desired level of between about 4.6 J/g to 35 J/g.

30 12. The method of claim 1, which further comprises adding external modifier to the catalyst in an amount sufficient to increase the crystallinity of the polyolefin polymers to a desired level of between about 15 J/g to 60 J/g.

13. The method of claim 12, which further comprises selecting the external modifier to be a silane component, selecting the desired level of crystallinity to be about 25 J/g to 55 J/g, and selecting the polyolefin polymer to have a melt
5 flow rate of between about 0.3 to 30 g / 10 min. at 230°C.

14. The method of claim 12, wherein ethylene is provided in an effective amount to preclude substantial modification by the external modifier of at least one physical property of the
10 polymer.

15. The method of claim 14, wherein the physical property is selected to include crystallinity of propylene domains in the polymer.
15

16. The method of claim 13, which further comprises selecting the melt flow rate of the polyolefin polymer to be between about 0.4 g / 10 min. to 60 g / 10 min.

17. The method of claim 16, which further comprises
20 selecting the melt flow rate of the polyolefin polymer to be between about 0.4 g / 10 min. to 15 g / 10 min.

18. The method of claim 1, which further comprises
25 reducing the stickiness to a sufficiently low level so that only between about 1 to 12 weight percent of the polyolefin polymer is soluble in methylethyl ketone.

19. The method of claim 18, which further comprises
30 reducing the stickiness to a sufficiently low level so that only between about 1 to 5 weight percent of the polyolefin polymer is soluble in methylethyl ketone.

20. The method of claim 1, which further comprises selecting the sufficient polymerization conditions to include a feed of a plurality of monomers having at least about 70 weight percent propylene, a temperature of about 130°F to 175°F, and a reactor pressure sufficient to maintain the propylene in a liquid phase.

21. The method of claim 1, which further comprises selecting the silane to have R_1 as a C_{5-12} cycloalkyl, R_2 as C_{1-6} alkyl, and R_3 and R_4 each as a C_{1-6} alkyl.

22. The method of claim 21, which further comprises selecting the silane to have R_1 as cyclohexyl, and R_2 , R_3 and R_4 each as methyl.

23. The method of claim 12, which further comprises selecting the external modifier to be a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, wherein R_1 and R_2 are each an H, C_{1-6} alkyl, aryl, C_{5-12} cycloalkyl, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-6} alkyl, or a mono- or di-substituted C_{1-6} alkyl.

24. The method of claim 1, which further comprises forming a molded product from the polymer.

25. The method of claim 24, which further comprises forming the molded product by injection molding or blow molding.

26. The method of claim 1, which further comprises forming a film having a thickness between about 0.5 mils to 10 mils from the polymer.

27. A polyolefin polymer produced by the process of claim 1.

28. The method of claim 24, wherein the polymer is formed to substantially maintain the same physical shape during steam autoclaving at a temperature of at least 100°C and at a pressure of at least atmospheric pressure.

29. A high-molecular weight average, polyolefin polymer having a heat of fusion of about 0.4 J/g to 75 J/g, a polydispersity index of less than about 10, and a melt flow rate of between about 0.3 g / 10 min. to about 30 g / 10 min. at 230°C, having a reduced stickiness.

30. A method of preparing polyolefin polymers which comprises:

preparing a pro-catalyst by mixing a magnesium halide, an aluminum halide, a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, an electron donor, and a tetravalent titanium halide to form a first mixture, wherein R_1 and R_2 are each an H, C_{1-6} alkyl, aryl, C_{5-12} cycloalkyl, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are each an H, C_{1-6} alkyl, or a mono- or di-substituted C_{1-6} alkyl;

adding a co-catalyst comprising an organometallic compound to the pro-catalyst to prepare a catalyst;

contacting a monomeric raw material and the catalyst under conditions sufficient to cause polymerization of the raw material to produce a polymerization product containing polyolefin polymers, wherein the catalyst reduces the stickiness of the resultant polyolefin polymers; and

recovering polyolefin polymers from the polymerization product.

31. A predominantly atactic polyolefin polymer-producing catalyst comprising:

a pro-catalyst comprising:

a magnesium halide,

5 an aluminum halide,

a titanium halide,

a nitrogen-based electron donor; and

a silane having the formula $R_1R_2Si(OR_3)(OR_4)$, wherein R_1 is a C_5 - C_{12} cycloalkane or a mono- or di-substituted C_5 - C_{12} cycloalkane, R_2 is an H, C_{1-6} alkyl, C_6 aryl, or C_5 -
10 C_{12} cycloalkane, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-6} alkane, or a mono- or di-substituted C_{1-6} alkane; and

a co-catalyst comprising an organometallic compound, or a reaction product thereof, wherein the catalyst may be used to
15 produce the predominantly atactic polyolefin polymers with reduced stickiness.

32. The catalyst of claim 31, wherein at least one halide of the magnesium halide, the aluminum halide, and the titanium
20 halide is a chloride; and R_2 is H or methyl.

33. The catalyst of claim 32, wherein the magnesium halide is magnesium dichloride, the aluminum halide is aluminum trichloride, and the titanium halide is titanium tetrachloride.

25 34. The catalyst of claim 31, wherein the electron donor comprises at least one of 2,6-lutidine, 6-chloro-2-picoline, 2,6-dichloropyridine, or mixtures thereof.

35. The catalyst of claim 31, wherein the electron donor
30 is a nitrogen-based compound, and the components are present in a molar ratio of Mg:Al:Si:N:Ti of about 8:0.01:0.01:0.2:1 to 80:30:0.5:1.2:1, wherein Mg, Al and Ti designate the magnesium,

aluminum and titanium halides, respectively, Si designates the silane component, and N designates the nitrogen-based electron donor.

5 36. The catalyst of claim 32, wherein R_1 is a C_{6-12} cycloalkane, R_2 is methyl, and R_3 and R_4 are each a C_{1-6} alkane.

10 37. The catalyst of claim 36, wherein R_1 is cyclohexyl, and R_2 , R_3 and R_4 each is methyl.

38. The catalyst of claim 31, further comprising an effective amount of an external modifier of a silane sufficient to increase the crystallinity of the polyolefin polymer.

15 39. A method of preparing a predominantly atactic polyolefin polymer-producing catalyst which comprises:

preparing a pro-catalyst by:

20 mixing a magnesium halide, an aluminum halide and a silane having the formula $R_1R_2Si(OR_3)(OR_4)$ to form a first mixture;

adding a nitrogen-based electron donor and a titanium halide to the first mixture; and

25 mixing the electron donor, titanium halide, and the first mixture to form a pro-catalyst mixture, wherein R_1 is a C_5-C_{12} cycloalkane or a mono- or di-substituted C_5-C_{12} cycloalkane, R_2 is an H, C_{1-6} alkyl, C_6 aryl, or

C_{5-12} cycloalkane, each of which may be unsubstituted, mono- or di-substituted, and R_3 and R_4 are H, C_{1-6} alkane, or a mono- or di-substituted

C_{1-6} alkane; and

30 adding a co-catalyst comprising an organometallic compound to the pro-catalyst to form a catalyst capable of reducing the stickiness of the predominantly atactic polyolefin polymers.

40. The method of claim 39, wherein the magnesium halide selected is magnesium dichloride, the aluminum halide selected is aluminum trichloride, the titanium halide selected is titanium tetrachloride, and R₂ is H or methyl.

5

41. The method of claim 40, wherein the electron donor to be added comprises at least one of 2,6-lutidine, 6-chloro-2-picoline, 2,6-dichloropyridine, or mixtures thereof.

10

42. The method of claim 39, wherein the electron donor is a nitrogen-based compound, and the pro-catalyst mixture is prepared with sufficient amounts of each component to provide a pro-catalyst having the components present in a molar ratio of Mg:Al:Si:N:Ti of about 8:0.01:0.01:0.2:1 to 80:30:0.5:1.2:1, wherein Mg, Al and Ti designate the magnesium, aluminum and titanium halides, respectively, Si designates the silane component, and N designates the nitrogen-based electron donor.

15

43. The method of claim 40, wherein the R₁ selected is cyclohexyl and R₂, R₃ and R₄ each is methyl.

20

44. The method of claim 39, wherein the magnesium halide and aluminum halide are solid when combined.

25

45. The method of claim 39, wherein the silane is a liquid that is sprayed into the mixture of magnesium halide and aluminum halide.

30

46. The method of claim 39, wherein the mixing occurs by ball milling and at least one of the mixing steps is temperature controlled to maintain the components and catalyst at a substantially constant temperature.

47. The method of claim 39, further comprising adding an external modifier in an amount sufficient to increase the crystallinity of the polyolefin polymers.

5 48. The method of claim 47, wherein the external modifier is selected to be a silane component and the amount of external modifier is selected to yield a catalyst capable of producing a polyolefin polymer having a low crystallinity of between about 15 J/g to 60 J/g and a melt flow rate of between about
10 0.3 to 30 g / 10 min. at 230°C.

49. The method of claim 48, wherein the melt flow rate is between about 0.4 to 15 g / 10 min.

15 50. A catalyst produced by the method of claim 39.

20

25

30

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US99/15235**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(6) : C08F 4/12, 4/16, 10/06; C08K 5/3432, 3/10

US CL : 526/157, 124.2, 141, 124.9, 125.3, 128, 158, 116, 351

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 526/157, 124.2, 141, 124.9, 125.3, 128, 158, 116, 351

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS

search terms: amorphous, atactic, polypropylene, Ziegler-Natta catalyst

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,347,158 A [KAUS et al] 31 August 1982, col. 6, lines 12-13; col. 19, lines 1-15; col. 20, lines 1-7.	1-30
Y	US 5,118,768 A [JOB et al] 02 June 1992, col. 10, lines 60-69; col. 11, lines 1-11.	1-30
Y	JP 62-115006 A [UBE INDUSTRIES LTD] 26 May 1987, page 2, lines 2-19; page 3, line 1.	1-50
A	US 5,565,532 A [BUSICO et al] 15 October 1996, col. 4, lines 44-55.	31-50



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
B earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

04 OCTOBER 1999

Date of mailing of the international search report

28 OCT 1999

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

LING-SIU CHOI

Telephone No. (703) 308-0651